



SPLENDORLUX PEARL

description

One-side Cast Coated boards, high gloss. Certify FSC, made with E.C.F. pulp. Light matt coating on reverse side. The Cast Coated side is surface coloured with pearly pigments and coated with a water-based varnish. The substance 300 g contain CTMP fibres in the inside layers which gives higher strength and thickness to the board. Available in nine colours.

range

size grain substance
70x100 LG 250 300

technical features
standard/instrument
unit of measure

| substance | VSA | Taber stiffness 15° | | breaking length | |
|------------------|--------------------|---------------------|-----------|-----------------|-----------|
| | | long±10% | cross±10% | long±10% | cross±10% |
| ISO 536 | ISO 534 | ISO 2493 | | ISO 1924 | |
| g/m ² | cm ³ /g | mN | | m | |
| 250 ± 5% | 1,20 | 160 | 81 | 7000 | 3000 |
| 300 ± 5% | 1,35 | 405 | 180 | 5800 | 3000 |

Relative Humidity 50% ± 5

ecological features



notes

Due to the presence of CTMP fibres in the inside layers, the 300g version do not comply with ISO 9706 “Long-Life” requirements. The product is completely biodegradable and recyclable. Special runs available upon request.

The Company reserves the right to modify the technological features of the product in relation to market requirements.



Splendorlux Pearl is particularly appreciated for converting uses in packaging, portfolios, soft covers, postcards, coordinated graphic materials and laminatings for the making of displays, wherever the need is to show a technical emphasis, a modern style and futuristic design.

applications

Splendorlux Pearl can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The surface is well sealed, therefore when printing in offset we suggest to employ inks for plastics and ensure more control at the pH and the conductivity of the fountain solution, in order to keep emulsions at minimum levels. Use of a moderate ink load will result in better control of setting; in this regard, good results are obtained with UCR or GCR grading to reduce the mass of ink transferred onto the paper; if necessary use anti set-off spray powder or add ink drier paste. When printing recto/verso it is advisable to print the matt side first to prevent damages to the other side. In hot foil stamping we recommend foil for plastic media.

printing
suggestions

Splendorlux Pearl gives good results with conventional or U.V. varnishing. Excellent results in plastic laminating. For folding operations is advisable prior scoring. In converting applications, due to the bigger granulometry of pearly pigments in comparison with the other ones, we suggest a particular attention to the rubbing. In folding and glueing processings we recommend high tack and adhesion glues, and we suggest the "milling" of the bonding area. If Splendorlux Pearl is plastic laminated with unsuitable adhesives, it might present an imperfect film anchorage.

converting
suggestions