



# STUCCO TINTORETTO

**description** Uncoated papers and boards made with E.C.F. pulp, certify FSC. Felt marked on both sides. Special “Stucco” treatment on both sides, allow a particularly bright and sharp printing. Available in “Gesso” colour.

**range**

size	grain	substance
72x101	LG	120 160 220 320

**technical features**  
standard/instrument  
unit of measure

substance	VSA	Taber stiffness 15°		breaking length	
ISO 536	ISO 534	ISO 2493		ISO 1924	
g/m <sup>2</sup>	cm <sup>3</sup> /g	mN		m	
		long±10%	cross±10%	long±10%	cross±10%
120 ± 3%	1,20	3,5	2	6500	3500
160 ± 3%	1,25	15	7	6500	3500
220 ± 4%	1,28	45	20	6100	3100
320 ± 5%	1,39	150	70	6000	3000

Brightness ISO 2470 (R457) - 94% ± 2  
Relative Humidity 50% ± 5

**ecological features**



ELEMENTAL  
CHLORINE  
FREE  
GUARANTEED



**notes** The product is completely biodegradable and recyclable. Special runs available upon request.



Envelopes available on stock.

The Company reserves the right to modify the technological features of the product in relation to market requirements.



Stucco Tintoretto papers and boards are ideal for any kind of publishing, packaging and commercial printing. They are held in high regard for de luxe publications, brochures and commercial printings - wherever the need is to exploit the features of a marked paper with the merits and the printing performance of coated paper.

**applications**

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. The characteristic felt marking requires specific printing pressure settings.

**printing suggestions**

Good results in varnishing and plastic laminating. The surface roughness typical of marked papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

**converting suggestions**